

PRODUCT	12040										
GLUE GUNS	simHM12 P 100 W simHM12 P 180 W simHM12 I 300 W simHM12 HD 400 W										
USE	Universal.										
PROPERTIES	Adhesive with clear appearance and good adhesion to many substrates like wood, cardboard, fabrics, glass, ceramics and certain plastics such as ABS, (hard) PVC, PS, PMMA and PC.										
DESCRIPTION	<table> <tr> <td>Basis:</td><td>EVA & synthetic resins</td></tr> <tr> <td>Composition:</td><td>Non-hazardous according to Directive 1999/45/CE</td></tr> <tr> <td>Color:</td><td>White / Traslucent</td></tr> <tr> <td>Diameter:</td><td>Ø 11,40 mm ± 0,40 mm</td></tr> <tr> <td>Long:</td><td>100 / 200 / 300 mm ± 5 mm</td></tr> </table>	Basis:	EVA & synthetic resins	Composition:	Non-hazardous according to Directive 1999/45/CE	Color:	White / Traslucent	Diameter:	Ø 11,40 mm ± 0,40 mm	Long:	100 / 200 / 300 mm ± 5 mm
Basis:	EVA & synthetic resins										
Composition:	Non-hazardous according to Directive 1999/45/CE										
Color:	White / Traslucent										
Diameter:	Ø 11,40 mm ± 0,40 mm										
Long:	100 / 200 / 300 mm ± 5 mm										
TECHNICAL DATA	<table> <tr> <td>Viscosity (180 °C):</td><td>10.000 ± 3.000 CP</td></tr> <tr> <td>Softening time:</td><td>87 ± 5 °C</td></tr> <tr> <td>Aplication temp:</td><td>170 °C - 210 °C</td></tr> <tr> <td>Open time:</td><td>40" - 50" (long)</td></tr> <tr> <td>Bond time:</td><td>20" - 25"</td></tr> </table>	Viscosity (180 °C):	10.000 ± 3.000 CP	Softening time:	87 ± 5 °C	Aplication temp:	170 °C - 210 °C	Open time:	40" - 50" (long)	Bond time:	20" - 25"
Viscosity (180 °C):	10.000 ± 3.000 CP										
Softening time:	87 ± 5 °C										
Aplication temp:	170 °C - 210 °C										
Open time:	40" - 50" (long)										
Bond time:	20" - 25"										
PACKAGING	Box 10 kg Pallet 600 kg										
INFORMATION	All components of this product comply with the requirements of Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food, and are approved for use in adhesives for indirect food contact by the Food & Drug Administration (Code of Federal Regulations, Title 21, Section 175.105 "Adhesives").										
REVIEW 5 / 5 / 2014											

COMERSIM S.A.U.

Pol. Ind. "Ampliación Comarca 1", Calle L 15 - 17
31160 ORKOIEN - Navarra - Spain

T +34 948 33 04 12
F +34 948 33 02 53

simes@grupodesa.es
www.simes.es

EXPORT

export@grupodesa.es
www.simes.es/hotmelt/en

T +34 948 33 52 66
F +34 948 33 02 53



Management
System
ISO 9001:2008

www.tuv.com
ID 1100008007

